



Standard Specification for Nickel-Chromium-Iron Alloys (UNS N06600, N06601, N06603, N06690, N06693, N06025, N06045, and N06696)* and Nickel- Chromium-Cobalt-Molybdenum Alloy (UNS N06617) Seamless Pipe and Tube¹

This standard is issued under the fixed designation B 167; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification² covers nickel-chromium-iron alloys (UNS N06600, N06601, N06603, N06690, N06693, N06025, N06045, and N06696)* and nickel-chromium-cobalt-molybdenum alloy (UNS N06617) in cold-worked annealed, hot-worked annealed, and hot-finished seamless pipe and tube intended for general corrosion resistant and heat resistant applications.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 The following safety hazards caveat pertains only to the test methods portion, Section 12, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:³

B 829 Specification for General Requirements for Nickel and Nickel Alloys Seamless Pipe and Tube

B 880 Specification for General Requirements for Chemical

Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys

E 8 Test Methods for Tension Testing of Metallic Materials

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E 38 Methods for Chemical Analysis of Nickel-Chromium and Nickel-Chromium-Iron Alloys⁴

E 527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

E 1473 Test Methods for Chemical Analysis of Nickel, Cobalt, and High-Temperature Alloys

2.2 Federal Standards:⁵

Fed. Std. No. 102 Preservation, Packaging and Packing Levels

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)

Fed. Std. No. 182 Continuous Identification Marking of Nickel and Nickel-Base Alloys

2.3 Military Standard:⁵

MIL-STD-129 Marking for Shipment and Storage

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *average diameter, n*—the average of the maximum and minimum outside diameters, as determined at any one cross section of the pipe or tube.

3.1.2 *pipe, n*—tube conforming to the particular dimensions commercially known as pipe sizes. See **Table X2.1**.

3.1.3 *seamless pipe or tube, n*—a pipe or tube produced with a continuous periphery in all stages of the operations.

3.1.4 *tube, n*—a hollow product of round or any other cross section having a continuous periphery.

4. Ordering Information

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for the safe and satisfactory

⁴ Withdrawn.

⁵ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://www.dodssp.daps.mil>.

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved March 15, 2008. Published March 2008. Originally approved in 1941. Last previous edition approved in 2006 as B 167 – 06.

* New designation established in accordance with Practice **E 527** and SAE J 1086, Practice for Numbering Metals and Alloys (UNS).

² For ASME Boiler and Pressure Vessel Code applications see related Specification SB-167 in Section II of that Code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

performance of material ordered under this specification. Examples of such requirements include, but are not limited to, the following:

- 4.1.1 *Alloy Name or UNS Number*—see [Table 1](#),
- 4.1.2 *ASTM Designation*, including year of issue,
- 4.1.3 *Condition* (see [Appendix X3](#)),
- 4.1.4 *Finish* (see [Appendix X3](#)),
- 4.1.5 *Dimensions*:
 - 4.1.5.1 *Tube*—Specify outside diameter and nominal or minimum wall,
 - 4.1.5.2 *Pipe*—Specify standard pipe size and schedule,
 - 4.1.5.3 *Length*—Cut to length or random,
- 4.1.6 *Quantity*—Feet or number of pieces,
- 4.1.7 *Hydrostatic Test or Nondestructive Electric Test*—Specify type of test (see [6.2](#)).
- 4.1.8 *Hydrostatic Pressure Requirements*—Specify test pressure if other than required by [12.3.1](#),
- 4.1.9 *Certification*—State if certification is required ([Section 15](#)),
- 4.1.10 *Samples for Product (Check) Analysis*—State whether samples for product (check) analysis should be furnished (see [5.2](#)),
- 4.1.11 *Purchaser Inspection*—If purchaser wishes to witness tests or inspection of material at place of manufacture, the purchase order must so state indicating which tests or inspections are to be witnessed ([Section 13](#)), and
- 4.1.12 *Small-Diameter and Light-Wall Tube (Converter Sizes)*—See [Appendix X1](#).

5. Chemical Composition

5.1 The material shall conform to the composition limits specified in [Table 1](#).

5.2 If a product (check) analysis is performed by the purchaser, the material shall conform to the product (check) analysis variations in [Specification B 880](#).

6. Mechanical Properties and Other Requirements

6.1 *Tensile Test*—The material shall conform to the tensile properties specified in [Table 2](#).

6.1.1 Tensile properties for material specified as small-diameter and light-wall tube (converter sizes) shall be as prescribed in [Table X1.1](#).

6.2 *Hydrostatic or Nondestructive Electric Test*—Each pipe or tube shall be subjected to either the hydrostatic test or the nondestructive electric test. The type of test to be used shall be at the option of the manufacturer, unless otherwise specified in the purchase order.

7. Dimensions and Permissible Variations

7.1 *Diameter, Wall Thickness, and Length*—The permissible variations in the outside diameter and wall thickness shall conform to the permissible variations prescribed in the Permissible Variations for Outside Diameter and Wall Thickness of Seamless Cold-Worked Pipe and Tube, Permissible Variations for Outside Diameter and Wall Thickness of Hot-Finished Tube, and Permissible Variations for Outside Diameter and Wall Thickness of Seamless Hot-Worked Pipe tables in [Specification B 829](#). The permissible variations in the length shall

conform to the permissible variations prescribed in the Permissible Variations in Length table in [Specification B 829](#).

7.2 Permissible variations for material specified as small-diameter and light-wall tube (converter size) shall conform to the permissible variations prescribed in [Table X1.2](#).

8. Workmanship, Finish, and Appearance

8.1 The material shall be uniform in quality and temper, smooth, commercially straight, and free of injurious imperfections.

9. Sampling

9.1 *Lot Definition*:

9.1.1 A lot for chemical analysis shall consist of one heat.

9.1.2 A lot for all other testing shall consist of all material from the same heat, nominal size (excepting length), and condition.

9.1.2.1 Where material cannot be identified by heat, a lot shall consist of not more than 500 lb (227 kg) of material in the same condition and nominal size (excepting length).

9.2 *Test Material Selection*:

9.2.1 *Chemical Analysis*—Representative samples from each lot shall be taken during pouring or subsequent processing.

9.2.1.1 Product (check) analysis shall be wholly the responsibility of the purchaser.

9.2.2 *Mechanical and Other Properties*—Samples of the material to provide test specimens for mechanical and other properties shall be taken from such locations in each lot as to be representative of that lot. Test specimens shall be taken from material in the final condition.

10. Number of Tests

10.1 *Chemical Analysis*—One test per lot.

10.2 *Tension*—One test per lot.

10.3 *Hydrostatic or Nondestructive Electric Test*—Each piece in each lot.

11. Specimen Preparation

11.1 *Room-Temperature Tension Specimen*—Material shall be tested in the direction of fabrication. Whenever possible, all pipe and tube shall be tested in full tubular size. When testing in full tubular size is not possible, longitudinal strip specimens, or the largest possible round specimen, shall be used. In the event of disagreement when full tubular testing is not possible, a longitudinal strip specimen with reduced gage length as contained in [Test Methods E 8](#) shall be used.

12. Test Methods

12.1 *Chemical Composition*—In case of disagreement, the chemical composition shall be determined in accordance with [Test Methods E 1473](#) or [Methods E 38](#). [Methods E 38](#) is to be used only for elements not covered by [Test Methods E 1473](#).

12.2 *Tension Test*—Tension testing shall be conducted in accordance with [Test Methods E 8](#).

12.3 *Hydrostatic Test*—Each pipe or tube with an outside diameter 1/8 in. (3 mm) and larger and with wall thickness of 0.015 in. (0.38 mm) and over shall be tested by the manufacturer to an internal hydrostatic pressure of 1000 psi (6.9 MPa)

TABLE 1 Chemical Requirements

Element	Composition Limits, %								
	Alloy N06025	Alloy N06045	Alloy N06600	Alloy N06601	Alloy N06603	Alloy N06617	Alloy N06690	Alloy N06693	Alloy N06696
Nickel	remainder ^A	45.0 min	72.0 min	58.0–63.0	remainder ^A	44.5 min	58.0 min	remainder ^A	remainder ^A
Chromium	24.0–26.0	26.0–29.0	14.0–17.0	21.0–25.0	24.0–26.0	20.0–24.0	27.0–31.0	27.0–31.0	28.0–32.0
Iron	8.0–11.0	21.0–25.0	6.0–10.0	remainder ^A	8.0–11.0	3.0 max	7.0–11.0	2.5–6.0	2.0–6.0
Manganese	0.15 max	1.0 max	1.0 max	1.5 max	0.15 max	1.0 max	0.5 max	1.0 max	1.0 max
Molybdenum	8.0–10.0	1.0–3.0
Cobalt	10.0–15.0
Aluminum	1.8–2.4	1.0–1.7	2.4–3.0	0.8–1.5	...	2.5–4.0	...
Carbon	0.15–0.25	0.05–0.12	0.15 max	0.10 max	0.20–0.40	0.05–0.15	0.05 max	0.15 max	0.15 max
Copper	0.1 max	0.3 max	0.5 max	1.0 max	0.50 max	0.5 max	0.5 max	0.5 max	1.5–3.0
Boron	0.006 max
Silicon	0.5 max	2.5–3.0	0.5 max	0.5 max	0.50 max	1.0 max	0.5 max	0.5 max	1.0–2.5
Sulfur	0.010 max	0.010 max	0.015 max	0.015 max	0.010 max	0.015 max	0.015 max	0.01 max	0.010 max
Titanium	0.1–0.2	0.1–0.25	0.6 max	...	1.0 max	1.0 max
Niobium	0.5–2.5	...
Phosphorous	0.020 max	0.020 max	0.020 max
Zirconium	0.01–0.10	0.01–0.10
Yttrium	0.05–0.12	0.01–0.15
Cerium	...	0.03–0.09

^A Element shall be determined arithmetically by difference.



TABLE 2 Mechanical Properties

Condition and Size	Tensile Strength, min psi (MPa)	Yield Strength (0.2 % offset), min, psi (MPa)	Elongation in 2 in. or 50 mm or 4D min,%
<i>UNS N06025:</i> Hot-worked annealed or cold worked annealed (all sizes)	98 000 (680)	39 000 (270)	30
<i>UNS N06045:</i> Hot-worked annealed or cold-worked annealed (all sizes)	90 000 (620)	35 000 (240)	35
<i>UNS N06600:</i> Hot-worked or hot- worked annealed: 5 in. (127 mm) in outside diameter and under	80 000 (550)	30 000 (205)	35
Over 5 in. (127 mm) in outside diameter	75 000 (515)	25 000 (170)	35
Cold-worked annealed: 5 in. (127 mm) in outside diameter and under	80 000 (550)	35 000 (240)	30
Over 5 in. (127 mm) in outside diameter	80 000 (550)	30 000 (205)	35
<i>UNS N06601:</i> Cold-worked annealed or hot-worked annealed: All sizes	80 000 (550)	30 000 (205)	30
<i>UNS N06603:</i> Hot-worked annealed or cold worked annealed (all sizes)	94 000 (650)	43 000 (300)	25
<i>UNS N06617:</i> Cold-worked annealed or hot-worked annealed: All sizes	95 000 (665)	35 000 (240)	35
<i>UNS N06690:</i> Hot-worked or hot- worked annealed: 5 in. (127 mm) in outside diameter and under	85 000 (586)	30 000 (205)	35
Over 5 in. (127 mm) in outside diameter	75 000 (515)	25 000 (170)	35
Cold-worked annealed: 5 in. (127 mm) in outside diameter and under	85 000 (586)	35 000 (240)	30
Over 5 in. (127 mm) in outside diameter	85 000 (586)	30 000 (205)	35
<i>UNS N06693:</i> Cold-worked annealed or hot- worked annealed: 5 in. (127 mm) in outside diameter and under	100 000 (690)	50 000 (345)	30
<i>UNS N06696</i> Cold-worked annealed (all sizes)	85 000 (586)	35 000 (240)	30

provided that the fiber stress calculated in accordance with the following equation does not exceed the allowable fiber stress, S , indicated as follows:

$$P = 2St/D \quad (1)$$

where:

P = hydrostatic test pressure, psi (or MPa),

S = allowable fiber stress, for material in the condition (temper) furnished as follows:

Hot-worked or hot-worked annealed:

UNS N06025	24 000 (165 MPa)
UNS N06045	22 500 (155 MPa)
UNS N06600	20 000 (140 MPa)
UNS N06601	20 000 (140 MPa)
UNS N06603	24 000 (165 MPa)
UNS N06617	23 700 (163 MPa)
UNS N06690	21 200 (146 MPa)
UNS N06693	25 000 (172 MPa)

Over 5 in. outside diameter:

UNS N06600	16 700 (115 MPa)
UNS N06690	16 700 (115 MPa)

Cold-worked annealed—All sizes:

UNS N06025	24 500 (169 MPa)
UNS N06045	22 500 (155 MPa)
UNS N06600	20 000 (140 MPa)
UNS N06601	20 000 (140 MPa)
UNS N06690	21 200 (146 MPa)
UNS N06693	21 200 (146 MPa)
UNS N06696	21 200 (146 MPa)

t = minimum wall thickness, in. (or mm), equal to the specified nominal wall minus the permissible minus wall tolerance, or the specified minimum wall thickness, and,

D = outside diameter of the pipe or tube, in. (or mm).

12.3.1 When so agreed upon between the manufacturer and purchaser, pipe or tube may be tested to 1½ times the allowable fiber stress given above.

12.3.2 If any pipe or tube shows leaks during hydrostatic testing, it shall be rejected.

12.4 *Nondestructive Electric Test*—Each pipe or tube shall be examined with a nondestructive electric test in accordance with Specification **B 829**.

12.5 *Rounding Method*—For purposes of determining compliance with the specified limits for requirements of the properties listed in the following table, an observed value, or a calculated value, shall be rounded as indicated below, in accordance with the rounding method of Practice **E 29**:

Test	Rounded Unit for Observed or Calculated Value
Chemical composition and tolerances (when expressed in decimals)	nearest unit in the last right-hand place of figures of the specified limit. If two choices are possible, as when the digits dropped are exactly a 5 or a 5 followed only by zeros, choose the one ending in an even digit with zero defined as an even digit.
Tensile strength, yield strength	nearest 1000 psi (6.9 MPa)
Elongation	nearest 1 %

13. Inspection

13.1 Inspection of the material shall be agreed upon between the purchaser and the supplier as part of the purchase contract.

14. Rejection and Rehearing

14.1 Material that fails to conform to the requirements of this specification may be rejected. Rejection should be reported to the producer or supplier promptly and in writing. In case of dissatisfaction with the results of the test, the producer or supplier may make claim for a rehearing.

15. Certification

15.1 When specified in the purchase order or contract, a manufacturer's certification shall be furnished to the purchaser stating that material has been manufactured, tested, and inspected in accordance with this specification, and that the test results on representative samples meet specification requirements. When specified in the purchase order or contract, a report of the test results shall be furnished.

16. Product Marking

16.1 The following information shall be marked on the material or included on the package, or on a label or tag attached thereto: The name of the material or UNS number, heat number, condition (temper), this specification number, the size, gross, tare and net weight, consignor and consignee address, contract or order number, or such other information as may be defined in the contract or order.

17. Keywords

17.1 seamless pipe; seamless tube; UNS N06025; UNS N06045; UNS N06600; UNS N06601; UNS N06603; UNS N06617; UNS N06690; UNS N06693; UNS N06696

SUPPLEMENTARY REQUIREMENTS

The following supplementary requirements shall apply only when specified by the purchaser in the inquiry, contract, or order, for agencies of the U. S. Government.

S1. Referenced Documents

S1.1 The following documents of the issue in effect on date of material purchased form a part of this specification to the extent referenced herein: Federal Standards 102, 123, and 182 and Military Standard **MIL-STD-129**.

S2. Quality Assurance*S2.1 Responsibility for Inspection:*

S2.1.1 Unless otherwise specified in the contract or purchase order, the manufacturer is responsible for the performance of all inspection and test requirements specified. Except as otherwise specified in the contract or purchase order, the manufacturer may use his own or any other suitable facilities for the performance of the inspection and test requirements unless disapproved by the purchaser at the time the order is placed. The purchaser shall have the right to perform any of the inspections or tests set forth when such inspections and tests are deemed necessary to ensure that the material conforms to prescribed requirements.

S3. Identification Marking

S3.1 All material shall be properly marked for identification in accordance with **Fed. Std. No. 182**, except that the ASTM specification number and the alloy number shall be used.

S4. Preparation for Delivery*S4.1 Preservation, Packaging, Packing:*

S4.1.1 *Military Agencies*—The material shall be separated by size, composition, grade, or class and shall be preserved and packaged, level A or C, packed level A, B, or C as specified in the contract or purchase order.

S4.1.2 *Civil Agencies*—The requirements of **Fed. Std. No. 102** shall be referenced for definitions of the various levels of packaging protection.

S4.2 Marking:

S4.2.1 *Military Agencies*—In addition to any special marking required by the contract or purchase order, marking for shipment shall be in accordance with **MIL-STD-129**.

S4.2.2 *Civil Agencies*—In addition to any special marking required by the contract or purchase order, marking for shipment shall be in accordance with **Fed. Std. No. 123**.

APPENDIXES

(Nonmandatory Information)

X1. CONVERTER SIZES

X1.1 Small-diameter and light-wall tube in outside diameters 1¼ in. (31.8 mm) and under may be furnished in the conditions listed in **Table X1.1** when so specified. The material is furnished in a limited range of sizes and the manufacturer

shall be consulted as to the various outside diameters and wall thicknesses that may be furnished. Material will have a bright finish. Such material shall conform to the applicable requirements in **Table X1.1** and **Table X1.2**.

TABLE X1.1 Mechanical Properties^A of Small-Diameter and Light-Wall Tubing (Converter Sizes)

Condition	Tensile Strength, psi (MPa)	Yield Strength (0.2 % offset) min, psi (MPa)	Elongation in 2 in. or 50 mm, min, %
<i>UNS N06600:</i> Annealed ^{B,C}	80 000 (550) to 110 000 (760)	35 000 (240)	30
Half-hard ^D	105 000 (725) min	55 000 (380)	13
Full-hard ^E	130 000 (895) min	105 000 (725)	4
<i>UNS N06601:</i> Annealed ^{B,C}	80 000 (550) to 110 000 (760)	30 000 (205)	30
<i>UNS N06601:</i> <i>UNS N06603:</i> Annealed ^{B,C}	94 000 (650) to 140 000 (965)	43000 (300)	25
<i>UNS N06617:</i> Annealed ^{B,C}	95 000 (665) to 110 000 (760)	35 000 (240)	35
<i>UNS N06690:</i> Annealed ^{B,C}	85 000 (586) to 110 000 (760)	35 000 (240)	30
Half-hard ^D	105 000 (725) min	55 000 (380)	13
Full-hard ^E	130 000 (895) min	105 000 (725)	4
<i>UNS N06025:</i> Annealed ^{B,C}	98 000 (680) to 125 000 (860)	39 000 (270)	30
<i>UNS N06045:</i> Annealed ^{B,C}	90 000 (620) to 120 000 (830)	35 000 (240)	35

^A Not applicable to outside diameters under 1/8 in. (3.2 mm) and wall thicknesses under 0.015 in. (0.38 mm).

^B This condition is sometimes designated as "No. 1 Temper."

^C The minimum tensile strength value applies only to tubing in straight lengths.

^D This condition is sometimes designated as "No. 2 Temper."

^E This condition is sometimes designated as "No. 3 Temper."

TABLE X1.2 Permissible Variations for Small-Diameter and Light-Wall Tube (Converter Sizes)^{A,B,C,D,E,F,G}

Specified Outside Diameter, in. (mm)	Outside Diameter		Inside Diameter		Wall thickness, %	
	+	-	+	-	+	-
		in. (mm)				
Under 3/32 (2.4)	0.002 (0.05)	0	0	0.002 (0.05)	10	10
3/32 to 3/16 (2.4 to 4.8), excl	0.003 (0.08)	0	0	0.003 (0.08)	10	10
3/16 to 1/2 (4.8 to 12.7), excl	0.004 (0.10)	0	0	0.004 (0.10)	10	10
1/2 to 1 1/4 (12.7 to 31.8), incl	0.005 (0.13)	0	0	0.005 (0.13)	10	10

^A *Ovality, Normal Wall Tube*—As-Drawn (No. 2 and 3) Tempers—Ovality will be held within the outside diameter tolerances shown in the table.

Annealed (No. 1) Temper—Ovality will be held within 2 % of the theoretical average outside diameter.

^B *Ovality, Light Wall Tube*—As-Drawn (No. 2 and 3) Tempers—Up to but not including 1 1/4 in. (31.8 mm) in outside diameter, ovality will be held within 2 % of the theoretical average outside diameter.

Annealed (No. 1) Temper—Ovality will be held within 3 % of the theoretical average outside diameter.

^C *Wall Tolerances, Light Wall Tube*—The plus and minus wall tolerance shown in the table shall apply down to and including 0.005 in. (0.13 mm) in wall thickness. For wall thicknesses less than 0.005 in. (0.13 mm), the tolerance shall be ± 0.005 in. (0.013 mm).

^D *Random Lengths:*

Where nominal random lengths on tubing 1/8 in. (3.2 mm) and larger in outside diameter are specified, a length of ± 3 1/2 ft (1.06 m) applies to the nominal length. This is a total spread of 7 ft (2.10 m).

Random lengths in sizes 1/8 in. (3.2 mm) and larger in outside diameter shall be subject to a length range of 5 to 24 ft (1.50 to 7.30 m). Long random lengths are subject to a range of 15 to 22 ft (4.57 to 6.70 m).

Random lengths in sizes up to but not including 1/8 in. (3.2 mm) in outside diameter, and fragile light-wall tubes over this outside diameter are subject to the length range of 1 to 15 ft (0.30 to 4.57 m).

^E *Cut Lengths*—Tolerances on cut lengths shall be in accordance with [Table X1.3](#).

^F *Straightness*—Round tubing is subject to a straightness tolerance of one part in 600 [equivalent to a depth of arc of 0.030 in. (0.76 mm) in any 3 ft (0.91 m) of length].

^G When specified, the tolerance spreads of this table may be applied as desired. However, when not specified, the tolerances in this table will apply. It should be noted that inside diameter tolerances are based upon the outside diameter range.

TABLE X1.3 Tolerances on Cut Lengths of Light-Wall Tube

Length, ft (m)	Tube Size, in. (mm)	Permissible Variations, in. (mm)	
		Over	Under
Under 1 (0.30)	up to 1.250 (31.8), incl	1/32 (0.8)	0 (0)
1 to 4 (0.30 to 1.22), incl	up to 1.250 (31.8), incl	1/16 (1.6)	0 (0)
Over 4 to 10 (1.22 to 3.0), incl	up to 1.250 (31.8), incl	3/32 (2.4)	0 (0)
Over 10 (3.0)	up to 1.250 (31.8), incl	3/16 (4.8)	0 (0)

X2. PIPE SCHEDULES

X2.1 The schedules of pipe shown in **Table X2.1** are regularly available. Other schedules may be furnished, and the manufacturer should be consulted. **Table X2.1** is published for information only.

TABLE X2.1 Pipe Schedules^A

Nominal Pipe Size, in.	Outside Diameter	Nominal Wall Thickness, in. (mm)			
		Schedule No. 5	Schedule No. 10	Schedule No. 40	Schedule No. 80
1/4	0.540(13.7)	...	0.065 (1.6)	0.088 (2.2)	...
3/8	0.675(17.1)	...	0.065 (1.6)	0.091 (2.3)	0.126 (3.2)
1/2	0.840(21.3)	0.065 (1.6)	0.083 (2.1)	0.109 (2.8)	0.147 (3.7)
3/4	1.050(26.7)	0.065 (1.6)	0.083 (2.1)	0.113 (2.8)	0.154 (3.9)
1	1.315(33.4)	0.065 (1.6)	0.109 (2.8)	0.133 (3.4)	0.179 (4.5)
1 1/4	1.660(42.2)	0.065 (1.6)	0.109 (2.8)	0.140 (3.6)	0.191 (4.8)
1 1/2	1.900(48.3)	0.065 (1.6)	0.109 (2.8)	0.145 (3.7)	0.200 (5.1)
2	2.375(60.3)	0.065 (1.6)	0.109 (2.8)	0.154 (3.9)	0.218 (5.5)
2 1/2	2.875(73.0)	0.083 (2.1)	0.120 (3.0)	0.203 (5.2)	0.276 (7.0)
3	3.500(88.9)	0.083 (2.1)	0.120 (3.0)	0.216 (5.5)	0.300 (7.6)
3 1/2	4.000(101.6)	0.083 (2.1)	0.120 (3.0)	0.226 (5.7)	0.318 (8.1)
4	4.500(114.3)	0.083 (2.1)	0.120 (3.0)	0.237 (6.0)	0.337 (8.6)
5	5.563(141.3)	0.258 (6.5)	...
6	6.625(168.3)	0.280 (7.1)	...

^A The pipe schedules shown above conform with standards adopted by the American National Standards Institute.

X3. CONDITIONS AND FINISHES NORMALLY SUPPLIED

X3.1 Scope

X3.1.1 This appendix lists the conditions and finishes in which pipe and tube (other than converter sizes) are normally supplied. These are subject to change, and the manufacturer should be consulted for the latest information available.

X3.2 Cold-Worked Tube and Pipe

X3.2.1 *Cold-Worked, Annealed, with Ground Outside Diameter*—The inside diameter may have a bright finish when material is annealed in a protective atmosphere; otherwise, the inside diameter is supplied descaled as necessary. It is available in sizes ½ to 4 in. (12.7 to 102 mm), inclusive, in outside diameter in both normal and heavy-wall tube, and pipe sizes, all schedules, of corresponding outside-diameter dimensions.

X3.2.2 *Cold-Worked, Annealed, and Pickled (Not Ground)*—Outside and inside diameter will have dull, matte (pickled) surfaces. It is available in sizes ½ to 6⅝ in. (12.7 to 168 mm), inclusive, in outside diameter in both normal and

heavy-wall tube, and pipe sizes, all schedules, of corresponding outside-diameter dimensions.

X3.3 Hot-Worked Tube

X3.3.1 *Hot-Worked or Hot-Worked-Annealed (Not Pickled) Tube*—Has an oxide surface resulting from the hot-working operation. Intended generally for machined parts where the oxide surface will be removed.

X3.3.2 *Hot-Worked or Hot-Worked-Annealed (Pickled) Tube*—Has the oxide surface removed on both outside and inside diameters by pickling. Surface may be spot ground for removal of minor surface imperfections at the manufacturer's option.

X3.3.3 *Hot-Worked or Hot-Worked-Annealed (Machined Outside and Inside Diameters) Tubes*—The outside and inside diameter surfaces are machined to specified dimensions. Minor surface imperfections may be spot ground for removal, at the manufacturer's option.

SUMMARY OF CHANGES

Committee B02 has identified the location of selected changes to this standard since the last issue (B 167 - 06) that may impact the use of this standard. (Approved March 15, 2008.)

(1) Added UNS N06696 to Title, 1.1, 12.3, Section 17, Table 1, and Table 2.

(2) Re-ordered the listing on alloys in 12.3, Table 1, and Table 2 in order of increasing UNS number.

Committee B02 has identified the location of selected changes to this standard since the last issue (B 167 - 05a) that may impact the use of this standard. (Approved December 1, 2006.)

(1) Revised the fiber stress for UNS N06693 in 12.3 and Table 2.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).