



Standard Specification for Niobium and Niobium Alloy Seamless and Welded Tubes¹

This standard is issued under the fixed designation B 394; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers wrought niobium and niobium alloy seamless and welded tubes as follows:

NOTE 1—Committee B10 has adopted “niobium” as the designation for Element No. 41, formerly named “columbium.”

- 1.1.1 R04200-Type 1—Reactor grade unalloyed niobium,
- 1.1.2 R04210-Type 2—Commercial grade unalloyed niobium,
- 1.1.3 R04251-Type 3—Reactor grade niobium alloy containing 1 % zirconium, and
- 1.1.4 R04261-Type 4—Commercial grade niobium alloy containing 1 % zirconium.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *The following precautionary caveat pertains only to the test methods portion of this specification. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

- 2.1 *ASTM Standards:*
 - B 391 Specification for Niobium and Niobium Alloy Ingots²
 - E 8 Test Methods for Tension Testing of Metallic Materials³
 - E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications⁴

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

¹ This specification is under the jurisdiction of ASTM Committee B10 on Reactive and Refractory Metals and Alloys and is the direct responsibility of Subcommittee B10.03 on Niobium and Tantalum.

Current edition approved Sept. 10, 2003. Published September 2003. Originally approved in 1989. Last previous edition approved in 1999 as B 394 - 99.

² *Annual Book of ASTM Standards*, Vol 02.04.

³ *Annual Book of ASTM Standards*, Vol 03.01.

⁴ *Annual Book of ASTM Standards*, Vol 14.02.

3.1.1 *lot*—a lot shall consist of all material produced from the same ingot at one time, with the same cross section, processed with the same nominal metallurgical parameters and heat treated at the same conditions.

4. Ordering Information

4.1 Orders for materials under this specification shall include the following information as applicable:

- 4.1.1 Type and grade (Section 1),
- 4.1.2 ASTM designation and year of issue,
- 4.1.3 Welding (Section 5),
- 4.1.4 Quantity in weight, number of pieces, and dimensions,
- 4.1.5 Chemistry (6.3),
- 4.1.6 Temper designation (Section 8),
- 4.1.7 Permissible variations in length and quantity or weight (9.2, 9.4, and Table 1^B),
- 4.1.8 Quality and finish (10.4),
- 4.1.9 Sampling (11.2),
- 4.1.10 Hydrostatic or pneumatic test (14.2),
- 4.1.11 Inspection (Section 15),
- 4.1.12 Required reports (Section 17), and
- 4.1.13 Additions to the specification and supplementary requirements, as required.

5. Materials and Manufacture

5.1 Material covered by this specification shall be made from ingots that conform to Specification B 391 and that are produced by vacuum or plasma arc melting, vacuum electron-beam melting, or a combination of these three methods.

5.2 Seamless tubes may be made by any seamless method that will yield a product meeting the requirements of this specification, such as, but not limited to, extrusion of billets with subsequent cold working by drawing, swaging, or rocking, with intermediate anneals, until the final dimensions are reached.

5.3 Welded tubing shall be made from flat-rolled products by an automatic or semiautomatic welding process with no addition of filler metal in the welding operation. Other methods of welding, such as the addition of filler metal or hand welding, may be employed if approved by the purchaser and tested by methods agreed upon between the manufacturer and the

**TABLE 1 Permissible Variations in Diameter and Wall Thickness
Measured at any Location^A**

Nominal Outside Diameter, in. (mm) ^B	Variation in Outside Diameter, Over and Under, in. (mm) ^B		Variation in Inside Diameter, Over and Under, in. (mm) ^C		Variation in Wall Thickness, Over and Under, % ^{C,D}
0.187 to 0.625 (4.7 to 15.9), excl	0.004	(0.010)	0.004	(0.010)	10
0.625 to 1.000 (15.9 to 25.4), excl	0.005	(0.13)	0.005	(0.13)	10
1.000 to 2.000 (25.4 to 50.8), excl	0.0075	(0.19)	0.0075	(0.19)	10
2.000 to 3.000 (50.8 to 76.2), excl	0.010	(0.25)	0.010	(0.25)	10
3.000 to 4.000 (76.2 to 101.6), excl	0.0125	(0.32)	0.0125	(0.32)	10

^AThese tolerances are applicable to only two dimensions, such as outside diameter and wall, or inside diameter and wall, or outside diameter and inside diameter.

^BFor applicable tolerances for very small tubes, less than 0.187 in. (4.9 mm) in outside diameter, or very thin wall tubes, less than 0.010 in. (0.25 mm), the producer should be consulted.

^CWhen tubes as ordered require wall thicknesses $\frac{3}{4}$ in. (19.05 mm) or over, or an inside diameter 60 % or less of the outside diameter, a wider variation in wall thickness is required. On such sizes, a variation in wall thickness of 12.5 % over and under will be permitted.

^DOvality measured at any cross section: For tubes with nominal wall thickness less than 3 % of the nominal outside diameter, the ovality tolerance is double the tolerance shown in the second and third columns.

purchaser. The manufacturer must use proper precautions to prevent contamination during welding.

6. Chemical and Hardness Requirements

6.1 The niobium and niobium alloy ingots and billets for conversion to finished products covered by this specification shall conform to the requirements for chemical composition and hardness as prescribed in Table 2 and Table 3.

6.2 The manufacturer's ingot analysis shall be considered the chemical analysis for products supplied under this specification, except for interstitials as specified in 6.3.

TABLE 2 Chemical Requirements

Element	Type 1 (Reactor Grade Unalloyed R04200	Type 2 (Commercial Grade Niobium) R04210	Type 3 (Reactor Grade Niobium—1 % Zirconium) R04251	Type 4 (Commercial Grade Niobium—1 % Zirconium) R04261
	Max Weight % (Except Where Otherwise Specified)			
Each ingot:				
Carbon	0.01	0.01	0.01	0.01
Nitrogen	0.01	0.01	0.01	0.01
Oxygen	0.015	0.025	0.015	0.025
Hydrogen	0.0015	0.0015	0.0015	0.0015
Zirconium	0.02	0.02	0.8 to 1.2 (range)	0.8 to 1.2 (range)
Tantalum	0.1	0.3	0.1	0.5
Iron	0.005	0.01	0.005	0.01
Silicon	0.005	0.005	0.005	0.005
Tungsten	0.03	0.05	0.03	0.05
Nickel	0.005	0.005	0.005	0.005
Molybdenum	0.010	0.020	0.010	0.050
Hafnium	0.02	0.02	0.02	0.02
Titanium	0.02	0.03	0.02	0.03
When specified:				
Boron	2 ppm	...	2 ppm	...
Aluminum	0.002	0.005	0.002	0.005
Beryllium	0.005	...	0.005	...
Chromium	0.002	...	0.002	...
Cobalt	0.002	...	0.002	...

TABLE 3 Brinell Hardness

	Type 1	Type 2	Type 3	Type 4
Maximum average	90	125	125	135
Maximum individual impression	105	150	140	150

6.3 When requested by the purchaser at the time of purchase, the manufacturer shall furnish a report certifying the values of the interstitial elements (C, O, N, H) as prescribed in Table 4 for each lot of material supplied.

7. Mechanical Requirements

7.1 The annealed materials supplied under this specification shall conform to the requirements for mechanical properties as specified in Table 5.

8. Temper Designations

8.1 Unless otherwise stated, the materials supplied under these specifications shall be in the fully annealed condition, that is, at least 90 % recrystallized.

8.2 Other temper designations, such as cold-worked temper or stress-relieved temper, can be specified as agreed upon between the purchaser and the manufacturer at the time of purchase.

**TABLE 4 Additional Chemical Requirements for Finished
Product (When Specified by Purchaser)**

Element	Type 1 (Reactor Grade Unalloyed Niobium) R04200	Type 2 (Commercial Grade Unalloyed Niobium) R04210	Type 3 (Reactor Grade Niobium—1 % Zirconium) R04251	Type 4 (Commercial Grade Niobium—1 % Zirconium) R04261
	Max Weight %			
Oxygen	0.0250	0.0400	0.0250	0.0400
Carbon	0.0100	0.0150	0.0100	0.0150
Nitrogen	0.0100	0.0100	0.0100	0.0100
Hydrogen	0.0015	0.0015	0.0015	0.0015

TABLE 5 Mechanical Properties^A for Material, Annealed Condition (90 % Minimum Recrystallized)

Grade	Ultimate Tensile Strength, min, psi (MPa)	Yield Strength (0.2 % offset), min, psi (MPa)	Elongation in 1-in. (25-mm) gage length, min, %
Type 1	18 000 (125)	10 500 (73)	25
Type 2	18 000 (125)	10 500 (73)	25
Type 3	28 000 (195)	18 000 (125)	20
Type 4	28 000 (195)	18 000 (125)	20

^ARefer to Section 13 for conditions of mechanical property tests.

9. Permissible Variations in Dimensions and Weight

9.1 *Diameter and Wall Thickness*—The permissible variations in diameter and wall thickness of the tubes shall not exceed those prescribed in Table 1.

9.2 *Length*—When tube is ordered cut to length, the useable length shall not be less than that specified, but a variation of + $\frac{1}{8}$ in. (3.18 mm) will be permitted for lengths up to 6 ft (1.8 m). For lengths over 6 ft, a variation of + $\frac{1}{4}$ in. (6.4 mm) will be permitted, unless otherwise specified at the time of purchase.

9.3 *Straightness*—The tube shall be free of bends or kinks, and the maximum bow shall not exceed values shown in Table 6.

9.4 *Quantity or Weight*—For orders requiring up to 100 ft (30.5 m) of finished tubing, the manufacturer may overship by 20 %. When the order is for quantities up to 1000 ft (305 m) or 1000 lb (453.6 kg), the manufacturer may overship by 10 %. The permissible overshipment shall be negotiated for orders larger than this quantity.

10. Quality and Finish

10.1 Finished niobium and niobium alloy tubes shall be free of injurious internal and external imperfections of a nature that will interfere with the purpose for which it was intended.

10.2 The finished tubes shall be visibly free of oxide, grease, oil, residual lubricants, and other extraneous materials.

10.3 The finished tubes shall be free of cracks, seams, slivers, burrs, blisters, and other injurious imperfections exceeding 10 % of the nominal wall thickness.

10.4 Methods of testing for these defects and standards of acceptability shall be as agreed upon between the manufacturer and the purchaser.

11. Sampling

11.1 Samples for chemical and mechanical testing shall be taken from the finished material after all metallurgical processing to determine conformity to this specification. The samples may be taken prior to final inspection and minor surface conditioning by abrasion and pickling, and shall be representative of the finished product.

TABLE 6 Straightness

Length, ft (m)	Maximum Curvature Depth of Arc
Over 3 to 6 (0.91 to 1.83), incl	$\frac{1}{8}$ in. (3.2 mm)
Over 6 to 8 (1.83 to 2.44), incl	$\frac{3}{16}$ in. (4.8 mm)
Over 8 to 10 (2.44 to 3.05), incl	$\frac{1}{4}$ in. (6.4 mm)
Over 10 (3.05)	$\frac{1}{4}$ in./any 10 ft (2.1 mm/m)

11.2 Care shall be exercised to ensure that the sample selected for testing is representative of the material and that it is not contaminated by the sampling procedure. If there is any question relating to the sampling technique or the analysis thereof, the methods of sampling and analysis shall be as agreed upon between the purchaser and the manufacturer.

12. Number of Tests and Retests

12.1 Two samples from each lot of tubes shall be tested for flare and tensile properties in the longitudinal direction.

12.2 When hydrostatic or pneumatic testing is required, all tubes in the lot shall be tested.

12.3 If end-product chemical tests are required (6.3), one chemical test shall be made from each lot of finished product.

12.4 *Retests*—If any sample or specimen exhibits obvious surface contamination or improper preparation, disqualifying it as a truly representative sample, it shall be discarded and a new sample or specimen substituted.

12.4.1 In case of a failure, retest two additional specimens. If both retest specimens conform to this specification, discard the original values and consider the material acceptable; otherwise, the lot shall be rejected or reworked and tested.

12.5 If the results of the final tube inspections are not in conformance with the requirements of this specification, the lot may be reworked at the option of the manufacturer. The lot shall be acceptable if results of all tests, after reworking, conform to this specification.

13. Significance of Numerical Limits

13.1 For the purposes of determining compliance with the specified limits for requirements of the properties listed in this specification, an observed value or a calculated value shall be rounded as indicated in accordance with the rounding method of Practice E 29.

14. Test Methods

14.1 *Tension Test*—Conduct tension tests in accordance with Test Methods E 8. Determine the yield strength by the 0.2 % offset method. Small size, 1-in. (25.4-mm) gage length specimens proportional to the standard specimen can be used. Determine tensile properties using a strain rate of 0.003 to 0.007 in./in.·min (mm/mm·min) through the yield point. After the yield strength has been exceeded, increase the cross-head speed to approximately 0.05 in./in.·min (mm/mm·min) to failure.

14.2 *Hydrostatic and Pneumatic Test*—These tests are optional. Should the purchaser require either or both of these tests on finished tubular product, the requirement must be agreed upon at the time of purchase. The cost of this special provision will be negotiated between the purchaser and the manufacturer at the time of purchase. The procedure for the hydrostatic test is outlined in 14.2.1, and the procedure for the pneumatic test is outlined in 14.2.2. If both tests are specified by the purchaser, the hydrostatic test will be done first.

14.2.1 *Hydrostatic Test*—Each tube so tested shall withstand without showing bulges, leaks, or other defects, an internal hydrostatic pressure that will produce in the tube wall

a stress of 75 % of the minimum specified yield strength at room temperature. This pressure shall be determined by the following equation:

$$P = 2St/D \quad (1)$$

where:

- P = minimum hydrostatic pressure, psi (or MPa),
- S = allowable fiber stress of 75 % of the minimum yield strength, psi (or MPa),
- t = average wall thickness of the tube, in. (or mm), and
- D = outside diameter of the tube, in. (or mm).

Maintain the test pressure for at least 10 s.

14.2.2 Pneumatic Test—Each tube so tested shall withstand an internal air pressure of 100 psi (.7 MPa) minimum for a minimum of 5 s without showing evidence of leakage. The test method used, for example, placing the tube under water or using the pressure differential method, shall permit easy visual detection of any leakage. Any evidence of leakage shall be cause for rejection of that tube.

14.3 Flare—A section of the finished tube shall be capable of being flared without cracking that is visible to the unaided eye. The flare shall be made with a tool having a 60° included angle until the outside diameter has been increased 15 %.

15. Inspection

15.1 If so specified on the purchase order, the purchaser or his representative may witness the testing and inspection of the material at the place of manufacture. In such cases, the purchaser shall state in his purchase order which tests he desires to witness. The manufacturer shall give ample notice to the purchaser as to the time and place of the designated test. If the purchaser's representative does not present himself at the agreed-upon time for the testing, and if no new date is set, the manufacturer shall consider the requirement for purchaser's inspection at the place of manufacture to be waived. When the inspector representing the purchaser does appear at the appointed place and time, the manufacturer shall afford him all reasonable facilities to see that the material is being furnished in accordance with this specification. This inspection shall be conducted so as not to interfere unnecessarily with production operations.

16. Rejection and Rehearing

16.1 Material that fails to conform to the requirements of this specification may be rejected. Rejection should be reported to the producer or supplier promptly and in writing. In case of dissatisfaction with the results of the test, the producer or supplier may make claim for a rehearing.

16.2 In the event of disagreement between the manufacturer and the purchaser about the conformance of the material to the requirements of this specification or any special test specified by the purchaser, a mutually acceptable referee shall perform the tests in question. The results of the referee's testing shall be used in determining conformance of the material to this specification.

17. Certification

17.1 When specified in the purchase order or contract, a producer's or supplier's certification shall be furnished to the purchaser that the material was manufactured, sampled, tested, and inspected in accordance with this specification and has been found to meet the requirements. When specified in the purchase order or contract, a report of the test results shall be furnished.

18. Product Marking

18.1 Each bundle, box, or carton shall be marked or tagged legibly and conspicuously with the number of this specification, type, temper, heat number, manufacturer's identification, nominal size, and the gross, net, and tare weights. If marking fluids are used, they shall be of such a nature as to be easily removed with cleaning solutions. The markings or their removal shall have no deleterious effect upon the material or its performance. The characters shall be sufficiently stable to withstand ordinary handling.

19. Packaging and Package Marking

19.1 All material shall be packed in such a manner as to ensure safe delivery to its destination when properly transported by any common carrier.

20. Keywords

20.1 niobium; niobium alloy; seamless tubes; seamless and welded tubes; welded tubes

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).